

Product data sheet SioxX[®]-Mag

Elkem ASA Silicon Products Drammensveien 169 P.O. Box 334 Skøyen NO-0213 OSLO Tel: +47 22 45 01 00 www.elkem.com

Description	SioxX [®] -Mag is designed for microsilica-gel bonded MgO castables. It enhances the rheological properties, reduces the water demand and increases the flow.	
Applications	Tailor-made product for microsilica-gel bonded MgO mixes and castables	
Benefits	 Reproducible wet-out, flow and set-time Easy to dose Easy to disperse in the dry and wet mix Robustness of mix through compatibility with other raw materials (dead burned MgO, fused MgO, sea water MgO, olivine and other different MgO sources 	
Technical data	Appearance	Grey powder
	Bulk density pH-value (10% solution)	400 - 650 kg/m ³ 3 - 5
	SiO₂ Al₂O₃ Proprietary additives	30 - 50 %w/w 30 - 50 %w/w 5 - 25 %w/w
	Recommended dosage	2 - 3 %w/w
Packaging	The product is available in 20 kg plastic bags, 600 kg per pallet. Please contact our sales representative for more details.	
Storage and handling	 Avoid dust generation Store in original packaging (or re-seal opened packages) under dry conditions >0°C. Shelf-life (best before) is 24 months from the date of production, if stored properly. 	
Health, safety & environment	Please consult our Product Safety information on our website: https://www.elkem.com/silicon-products/refractories/specialties/sioxx-specialities/pds/.	
Sustainability	For Elkem, sustainability is central to our business strategy. Our mission is to provide advanced material solutions shaping a better and more sustainable future, adding value to our stakeholders globally. We are committed to reduction in embodied carbon emission. For further information, please visit <u>www.elkem.com/sustainability/</u> or contact us to learn more about our sustainability roadmap.	
Additional information and contact	For further information, please contact our local sales representative. Our specialists will assist you in solving individual problems.	

This product data sheet is property of Elkem ASA and may not without its written permission be used, copied or made available to others. The receiver is responsible for any misuse. © Copyright Elkem ASA